


M60 ULTRA LOW PROFILE SPRAY CONTACT ADHESIVE

DATA SHEET
TensorGrip



As part of our **MARINE** range, **M60** is a mist spray adhesive designed for use on cabinets and walls using the substrates listed above.

PRODUCT DESCRIPTION

TensorGrip M60 is a Low VOC, LEED and California Compliant post-formable contact adhesive; designed for maximum smoothness with many materials used in boat outfitting.

ADVANTAGES

- Fast. High tack
- Post-formable
- Doesn't telegraph through substrates
- Excellent high coverage
- Low VOC California compliant (SCAQMD Rule 1168)
- 80% of final strength achieved immediately
- Full strength achieved in 24 hours
- Over 200°F (95°C) temperature resistant

DIRECTIONS FOR USE

- **TensorGrip® M60** is designed as a portable, self-contained spray system for field or shop applications.
- Apply adhesive to one or both surfaces to be mated, at 80% to 100% coverage.
- Allow enough time (2-4 minutes or until dry to the touch) for the adhesive to become tacky before bonding.
- Parts should be mated with as much pressure as practical.
- Normal coverage required with mist spray pattern is over 80%; however, porous surfaces may need a second coat.
- Initial bond is strong enough to allow cutting or trimming immediately, although ultimate strength is achieved in 1-3 days.
- Canister system will spray adequately above 60° F. Canister system should be kept in warm area. In the event that the canister gets abnormally chilled, freezes or gives poor or sputtering spray, it should be warmed up before continued usage. Warming canister by immersion in warm water is recommended.
- Notice!!! Do not store at temperatures over 120° F.

CANISTER STORAGE/CHANGE OVER

- If you choose to leave the hose and spray gun on the canister, leave the valve on the canister open. Do not disconnect the hose/gun from the canister. Close and lock the spray gun.
- To change or disconnect canister: turn canister valve to the off position, spray out remaining adhesive left in the hose, disconnect the spray hose and gun from the canister.
- Reconnect the spray hose to a new canister of adhesive. OR if you are NOT connecting to a new canister, connect hose to canister of cleaning solvent (sold separately) and spray out until liquid is clear which indicates that the hose and gun is clean.

QUIN GLOBAL AU

30 Faunce Street, PO Box 6196, Queanbeyan, Australia, NSW 2620
PH: +61 2 6175 0574 | sales.au@quin-global.com | www.quiringlobal.com



Tensor

M60 ULTRA LOW PROFILE SPRAY CONTACT ADHESIVE

DATA SHEET
Tensorgrip

CHEMICAL TECHNICAL DATA

TYPICAL PROPERTIES

• Total Solids	25-31%
• VOC Content	37 g/L
• Color	Clear, Blue
• System Flammability	Flammable adhesive; Non-Flammable propellant
• Solvent System	Methyl Acetate
• Dry time	2-4 mins dependent on temp & humidity
• Open time	Long
• Shelf Life	18 months from date of manufacture

PACKAGING

• 7L	Disposable Canister
• 22L	Disposable Canister
• 108L	Returnable Canister
• 216L	Returnable Canister

STORAGE

HANDLING & STORAGE

- Consult Material Safety Data Sheet prior to use.
- Do not store at temperatures over 120°F/50°C.
- Avoid exposure to direct sunlight.
- Do not store directly on concrete floor.
- Always store above 60°F/15°C
- When connected, keep valve open and hose pressurized at all times
- Always test our adhesives to determine suitability for your particular application prior to use in production

DISCLAIMER OF WARRANTY: Quin Global makes neither warranty of merchantability or fitness for any use nor any other warranty, express or implied, in the sales of its products. Buyer assumes all risk and liability for the results obtained by the use of its products, whether used singly or in combination with other products.

QUIN GLOBAL AU

30 Faunce Street, PO Box 6196, Queanbeyan, Australia, NSW 2620
PH: +61 2 6175 0574 | sales.au@quin-global.com | www.quinlobal.com



Tensor